

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 9/14, 9/51	A1	(11) International Publication Number: WO 96/00567 (43) International Publication Date: 11 January 1996 (11.01.96)
(21) International Application Number: PCT/US95/07406 (22) International Filing Date: 9 June 1995 (09.06.95) (30) Priority Data: 08/267,082 28 June 1994 (28.06.94) US (71) Applicant (for all designated States except US): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): WONG, Sui, Ming [US/US]; 159 Deer Drive, Collegeville, PA 19426 (US). (74) Agent: ROSENSTEIN, Arthur, H.; 343 State Street, Rochester, NY 14650-2201 (US).		(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SG, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: BUTYLENE OXIDE-ETHYLENE OXIDE BLOCK COPOLYMER SURFACTANTS AS STABILIZER COATINGS FOR NANOCRYSTAL FORMULATION (57) Abstract This invention provides a composition comprised of nanoparticles containing a therapeutic or diagnostic agent having a nonionic polymeric surfactant as a surface modifier adsorbed on the surface thereof, the surfactant being a block copolymer of ethylene oxide and butylene oxide and a method of making such nanoparticles. The compositions exhibit reduced macrophage uptake and improved toxicological profiles and facilitate particle size reduction such that milling time can be reduced and/or sterile filtration of the nanoparticles can be accomplished.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

BUTYLENE OXIDE-ETHYLENE OXIDE BLOCK COPOLYMER
SURFACTANTS AS STABILIZER COATINGS FOR
NANOCRYSTAL FORMULATION

5

Field of the Invention

This invention relates to therapeutic and diagnostic
10 compositions containing a surfactant and to a method for the
preparation thereof.

Background of the Invention

15 U.S. Patent No. 5,145,684 discloses particles of a drug
substance having a surface modifier adsorbed on the surface
thereof and methods for the preparation thereof by wet
grinding. These particles have demonstrated significant
pharmaceutical utility. Suitable surface modifiers described
20 include various polymers. The preferred surface modifiers
disclosed include Pluronic F68 and F108, which are block
copolymers of ethylene oxide and propylene oxide and Tetronic
908, which is tetrafunctional block copolymers derived from
sequential addition of ethylene oxide and propylene oxide to
25 ethylene diamine.

U.S. Patent No. 5,318,767 discloses x-ray contrast
compositions comprising particles of a x-ray contrast agent
having a surface modifier adsorbed on the surface thereof and
methods for the preparation thereof by wet grinding. The
30 above-noted surface modifiers are also disclosed as being
useful therein. These x-ray contrast compositions have
demonstrated remarkable utility in x-ray medical diagnostic
imaging procedures.

P. Sampotdar et al., U.S. Patent Application Serial No.
35 07/988,564 filed December 10, 1992, discloses therapeutic and
diagnostic compositions with Olin-10 G, i.e., p-

-2-

isononylphenoxypoly(glycidol) having improved autoclave stability.

However, some of the above-described polymeric surfactants have demonstrated less than superior toxicological profiles, for example, in a "smudge cell" assay. In addition, these prior art surfactant coatings, on some occasions, have exhibited less than desirable inhibition of macrophage uptake.

Furthermore, sterilization of therapeutic and diagnostic agents in nanoparticulate form stabilized by a surface modifier is difficult. Filtration using a filter of 0.22 μm mesh size is sufficient to remove most bacteria and viruses, but the nanoparticles, due to their sizes, cannot be sterile filtered without accounting for substantial drug losses.

Moreover, the wet grinding methods described in the patents noted above often entail grinding for days or even weeks which can be undesirable, e.g., from the standpoint of process scale-up.

Consequently, it would be highly desirable to provide surfactant coatings for nanoparticles which reduce the smudge cell effect, inhibit macrophage uptake facilitate particle size reduction such that milling time can be reduced and/or sterile filtration of the nanoparticles can be accomplished without substantial particle losses.

25

Summary of the Invention

We have discovered surfactant coatings for nanoparticles which reduce the smudge cell effect, inhibit macrophage uptake and unexpectedly facilitate particle size reduction.

More specifically, in accordance with this invention, there is provided a composition comprised of nanoparticles containing a therapeutic or diagnostic agent having a nonionic polymeric surfactant as a surface modifier adsorbed on the surface thereof, wherein said surfactant is a block copolymer of ethylene oxide and butylene oxide.

-3-

It is an advantageous feature of this invention that surfactants are provided for nanoparticle compositions which exhibit a reduced smudge cell effect.

It is another advantageous feature of this invention that nanoparticle compositions are provided which inhibit macrophage uptake.

Yet another advantageous feature of this invention is that nanoparticle compositions are provided in a narrow particle size distribution.

Still another advantageous feature of this invention is that a surfactant coating is provided for nanoparticles which facilitates particle size reduction, thus reducing milling time and potentially enabling sterile filtration of the nanoparticles to be accomplished without substantial particle losses.

These and other advantages will become readily apparent upon reference to the following description of preferred embodiments.

20

DESCRIPTION OF PREFERRED EMBODIMENTS

This invention is described hereinafter primarily in connection with nanoparticles containing a therapeutic or diagnostic agent having a nonionic block copolymer of ethylene oxide or a butylene oxide as a surface modifier adsorbed on the surface thereof. In addition, the invention is believed to be useful in composition with nanoparticles containing, e.g., photographic and cosmetic agents, and with other nonionic polymeric surface modifiers containing blocks of ethylene oxide and other hydrophobes such as pentylene oxide, hexylene oxide, cyclohexylene oxide and styrene oxide.

Surfactants useful herein are nonionic block copolymers. Preferred surfactants contain at least one polyethylene oxide (PEO) block as the hydrophilic portion of the molecule and at least one polybutylene oxide (PBO) block as the hydrophobic portion of the surfactant. Particularly preferred surfactants are diblock, triblock, and higher block


-4-

copolymers of ethylene oxide and butylene oxide, such as are represented, for example, by the following structural formula:

(-PEO-)(-PBO-); (-PEO-)(-PBO-)(-PEO-); and (-PEO-)(-PBO-)
 5 (-PEO-)(-PBO-).

Highly preferred surfactants include triblock copolymers of the structure (-PEO-)(-PBO-)(-PEO-) having molecular weights of 3800 and 5000 which are commercially available from Dow Chemical, Midland, Michigan, are hereinafter referred to as
 10 B20-3800 and B20-5000. These surfactants contain about 80% by weight PEO.

In a preferred embodiment, the surfactant is a triblock polymer having the structure:



15

wherein R is H or an active hydrogen group, such as alkyl, aryl, carboxyalkyl or carboxyaryl, x is 15-700, y is 5-200 and z is 15-700. In particularly preferred embodiments, the surfactant has a molecular weight of 1,000-50,000, preferably
 20 2,000-40,000 and preferably 3,000-30,000. In preferred embodiments, the polymer comprises at least about 50%, and more preferably at least about 60% by weight ethylene oxide units. The reason for this is that the presence of a major weight proportion of hydrophilic units confers aqueous
 25 solubility to the polymer.

While applicants do not wish to be bound by theoretical mechanisms, it is believed that the presence of the butylene oxide hydrophobe in the polymer chain increases lipophilic interaction between surfactant and the hydrophobic
 30 therapeutic or diagnostic agent, thus facilitating the ability of the surfactant to coat the surface of the particulate therapeutic or diagnostic agent.

This surface modifier is commercially available and/or can be prepared by techniques known in the art.

-5-

The nanoparticles useful in the practice of this invention can be prepared according to the methods disclosed in U.S. Patent No. 5,145,684 and U.S. Patent No. 5,318,767.

Briefly, a method for the preparation of a nanoparticle composition according to this invention includes the steps of introducing a diagnostic or therapeutic agent, a liquid medium, grinding media, and optionally, a surface modifier into a grinding vessel; wet grinding to reduce the particle size of the agent to less than about 1000 nm; and separating the particles and the liquid medium from the grinding vessel and grinding media, for example, by suction, filtration or evaporation. If the surface modifier is not present during wet grinding, it can be admixed with the particles thereafter. The liquid medium, most often water, can serve as the pharmaceutically acceptable carrier. The method preferably is carried out under aseptic conditions.

A general procedure for preparing the particles useful in the practice of this invention follows. The therapeutic or diagnostic agent selected is obtained commercially and/or prepared by techniques known in the art, in a conventional coarse form. It is preferred, but not essential, that the particle size of the coarse therapeutic or diagnostic substance selected be less than about 100 μm as determined by sieve analysis. If the coarse particle size of that agent is greater than about 100 μm , then it is preferred that the coarse particles of the therapeutic or diagnostic agent be reduced in size to less than 100 μm using a conventional milling method such as airjet or fragmentation milling.

The coarse therapeutic or diagnostic agent selected can then be added to a liquid medium in which it is essentially insoluble to form a premix. The concentration of the therapeutic or diagnostic agent in the liquid medium can vary from about 0.1-60%, and preferably is from 5-30% (w/w). It is preferred, but not essential, that the surface modifier be present in the premix. The concentration of the surface modifier can vary from about 0.1 to 90%, and preferably is 1-75%, more preferably 2-50% and most preferably 5-45% by

-6-

weight based on the total combined weight of the drug substance and surface modifier. The apparent viscosity of the premix suspension is preferably less than about 1000 centipoise.

- 5 The premix can be used directly by wet grinding to reduce the average particle size in the dispersion to less than 1000 nm. It is preferred that the premix be used directly when a ball mill is used for attrition. Alternatively, the therapeutic or diagnostic agent and,
10 optionally, the surface modifier, can be dispersed in the liquid medium using suitable agitation, e.g., a roller mill or a Cowles type mixer, until a homogeneous dispersion is observed in which there are no large agglomerates visible to the naked eye. It is preferred that the premix be subjected
15 to such a premilling dispersion step when a recirculating media mill is used for attrition.

- Wet grinding can take place in any suitable dispersion mill, including, for example, a ball mill, an attritor mill, a vibratory mill, a planetary mill and media mills such as a
20 sand mill and a bead mill. A media mill is preferred due to the relatively shorter milling time required to provide the intended result, i.e., the desired reduction in particle size. For media milling, the apparent viscosity of the premix preferably is from about 100 to about 1000 centipoise.
25 For ball milling, the apparent viscosity of the premix preferably is from about 1 up to about 100 centipoise. Such ranges tend to afford an optimal balance between efficient particle fragmentation and media erosion.

- The grinding media for the particle size reduction step
30 can be selected from rigid media preferably spherical or particulate in form having an average size less than about 3 mm and, more preferably, less than about 1 mm. Such media desirably can provide the particles of the invention with shorter processing times and impart less wear to the milling
35 equipment. The selection of material for the grinding media is not believed to be critical. However, media with higher density, e.g., glass (2.6 g/cm³), zirconium silicate (3.7

-7-

g/cm³), and zirconium oxide (5.4 g/cm³), are generally preferred for more efficient milling. Zirconium oxide, such as 95% ZrO stabilized with magnesia, zirconium silicate, and glass grinding media provide particles having levels of contamination which are believed to be acceptable for the preparation of therapeutic or diagnostic compositions. However, other media, such as stainless steel, titania, alumina, and 95% ZrO stabilized with yttrium, are believed to be useful. In addition, polymeric media having a density typically from 1 to 2 g/cm³ are also expected to be useful under certain milling conditions. The grinding media can be a polymeric resin such as described in European Patent Application Serial No. 600,528.

The attrition time can vary widely and depends primarily upon the particular wet grinding mill selected. For ball mills, processing times of up to five days or longer may be required. On the other hand, processing times of less than 1 day (residence times of about one minute up to several hours) have provided the desired results using a high shear media mill.

The particles must be reduced in size at a temperature which does not significantly degrade the therapeutic or diagnostic agent. Processing temperatures of less than about 30-40°C are ordinarily preferred. If desired, the processing equipment can be cooled with conventional cooling equipment. The method is conveniently carried out under conditions of ambient temperature and at processing pressures which are safe and effective for the milling process. For example, ambient processing pressures are typical of ball mills, attritor mills and vibratory mills. Processing pressures up to about 20 psi (1.4 kg/cm²) are typical of media milling.

The surface modifier, if not present in the premix, must be added to the dispersion after attrition in an amount as described for the premix. Thereafter, the dispersion can be mixed, e.g., by shaking vigorously. Optionally, the dispersion can be subjected to a sonication step, e.g., using an ultrasonic power supply. For example, the dispersion can

-8-

be subjected to ultrasonic energy having a frequency of 20-80 kHz for a time of about 1 to 120 seconds.

The relative amount of therapeutic or diagnostic agent and surface modifier can vary widely and the optimal amount of the surface modifier can depend, for example, upon the particular therapeutic or diagnostic agent and surface modifier selected, the critical micelle concentration of the surface modifier if it forms micelles, the hydrophilic lipophilic balance (HLB) of the stabilizer, the melting point of the stabilizer, its water solubility, the surface tension of water solutions of the stabilizer, etc. The surface modifier preferably is present in an amount of about 0.1-10 mg per square meter surface area of the therapeutic or diagnostic agent. The surface modifier can be present in an amount of 0.1-90%, preferably 1-75%, more preferably 2-50%, and most preferably 5-45% by weight based on the total weight of the dry particle. The surface modifier preferably is present in an amount exceeding the critical miscelle concentration.

Therapeutic and diagnostic agents useful in the composition of the present invention include those disclosed in U.S. Patent No. 5,145,684, and U.S. Patent No. 5,318,767 whose disclosures are incorporated herein by reference. Preferred diagnostic agents include the x-ray imaging agent ethyl 3,5-diacetamido-2,4,6-triiodobenzoate, (compound A); 6-ethoxy-6-oxohexyl-3,5-bis(acetamido)-2,4,6-triiodobenzoate (compound B); ethyl-2-(3,5-bis(acetamido)-2,4,6-triiodobenzoyloxy)butyrate; ethyl diatrizoxyacetate; ethyl 2-(3,5-bis(acetamido)-2,4,6-triiodobenzoyloxy)propionate; N-ethyl 2-(3,5-bis(acetamido)-2,4,6-triiodobenzoyloxy)acetamide; isopropyl 2-(3,5-bis(acetamido)-2,4,6-triiodobenzoyloxy)acetamide; diethyl 2-(3,5-bis(acetamido)-2,4,6-triiodobenzoyloxy)malonate; and ethyl 2-(3,5-bis(acetamido)-2,4,6-triiodobenzoyloxy)phenylacetate.

A method for the preparation of a nanoparticle composition according to this invention includes the steps of introducing a therapeutic or diagnostic agent, a liquid

-9-

medium, grinding media, and optionally, a surface modifier into a grinding vessel; wet grinding to reduce the particle size of the therapeutic or diagnostic agent to less than about 1000 nm; and separating the particles and the liquid medium from the grinding vessel and grinding media, for example, by suction, filtration or evaporation. If the surface modifier is not present during wet grinding, it can be admixed with the particles thereafter. The liquid medium, most often water, can serve as the pharmaceutically acceptable carrier. The method can be carried out under aseptic conditions. Thereafter, the nanoparticle composition preferably is subjected to a sterilization process.

As noted elsewhere herein, sterile filtration will not provide adequate sterilization for nanoparticles without causing significant loss of active material. Although the compositions of this invention can be sterile filtered, other methods of sterilization can also be employed. For example, steam or moist heat sterilization at temperatures of about 121°C for a time period of about 20 minutes can be used. At altitudes near sea level, such conditions are attained by using steam at a pressure of 15 pounds per square inch (psi) in excess of atmospheric pressure.

Dry heat sterilization may also be performed, although the temperatures used for dry heat sterilization are typically 160°C for time periods of 1 to 2 hours.

In preferred embodiments, the therapeutic or diagnostic agent in the form of surface modified nanoparticles can be associated with a cloud point modifier to enhance stability during steam heat autoclaving, i.e., the cloud point modifier can reduce particle aggregation during heat sterilization. Preferred cloud point modifiers include nonionic cloud point modifiers, such as polyethylene glycols such PEG 400, propylene glycol, ethanol, hydroxypropylcyclodextrin and glycerol; ionic cloud point modifiers, such as those described in U.S. Patent No. 5,298,262 including dialkylesters of sodium sulfosuccinic acid such as the dioctylester of sodium sulfosuccinic acid (DOSS); and charged

-10-

phospholipids, such as diacylphosphatidyl glycerol and dimyristoylphosphatidyl glycerol. The cloud point modifier can be present in an amount of 0.005-50%, preferably 0.01-30% and more preferably 0.05-20% by weight based on the total weight of the nanoparticle composition.

Therapeutic and diagnostic compositions according to this invention include the particles described above and a pharmaceutically acceptable carrier therefor. Suitable pharmaceutically acceptable carriers are well known to those skilled in the art. These include non-toxic physiologically acceptable carriers, adjuvants or vehicles for parenteral injection, for oral administration in solid or liquid form, for rectal administration, and the like. A method of treating a mammal in accordance with this invention comprises the step administering to the mammal in need of treatment an effective amount of the above-described therapeutic composition. The selected dosage level of the therapeutic substance for treatment is effective to obtain a desired therapeutic response for a particular composition and method of administration. The selected dosage level therefore, depends upon the particular drug substance, the desired therapeutic effect, on the route of administration, on the desired duration of treatment and other factors.

In a preferred embodiment, the diagnostic compound is an iodinated x-ray contrast agent, such as an iodinated x-ray contrast agent. Thus, the diagnostic compositions of this invention conclude an x-ray contrast composition comprising particles containing an x-ray contrast agent and a physiologically acceptable carrier therefor. For example, the particles can be dispersed in an aqueous liquid which serves as the carrier for the x-ray contrast agent. Other suitable carriers include liquid carriers such as mixed aqueous and nonaqueous solvents, such as alcohol; gels; gases, such as air; and powders.

The x-ray contrast compositions can comprise from about 1-99.9, preferably 2-45 and more preferably 10-30% by weight of the above-described particles, the remainder of the

-11-

composition being the carrier, additives and the like. Compositions up to about 100% by weight of the particles are contemplated when the composition is in a lyophilized form.

The x-ray contrast composition can contain one or more
5 conventional additives used to control and/or enhance the properties of the x-ray contrast agent. For example, thickening agents such as dextran or human serum albumin, buffers, viscosity regulating agents, suspending agents, peptizing agents, anti-clotting agents, mixing agents, and
10 other drugs and the like can be added. A partial listing of certain specific additives includes gums, sugars such as dextran, human serum albumin, gelatin, sodium alginate, agar, dextrin, pectin and sodium carboxymethyl cellulose. Such additives, surface active agents, preservatives and the
15 like can be incorporated into the compositions of the invention.

A method for diagnostic imaging for use in medical procedures in accordance with this invention comprises administering to the body of a test subject in need of an x-
20 ray an effective contrast producing amount of the above-described x-ray contrast composition. In addition to human patients, the test subject can include mammalian species such as rabbits, dogs, cats, monkeys, sheep, pigs, horses, bovine animals and the like. Thereafter, at least a portion of the
25 body containing the administered contrast agent is exposed to x-rays to produce an x-ray image pattern corresponding to the presence of the contrast agent. The image pattern can then be visualized. For example, any x-ray visualization technique, preferably, a high contrast technique such as
30 computed tomography, can be applied in a convention manner. Alternatively, the image pattern can be observed directly on an x-ray sensitive phosphor screen-silver halide photographic film combination.

The compositions of this invention can be administered
35 by a variety of routes depending on the type of procedure and the anatomical orientation of this tissue being examined. Suitable administration routes include intravascular

-12-

(arterial or venous) administration by catheter, intravenous injection, rectal administration, subcutaneous administration, intramuscular administration, intralesional administration, intrathecal administration, intracisternal administration, oral administration, administration via inhalation, administration directly into a body cavity, e.g., arthrography, and the like. In addition to preferred applications, i.e., for blood pool, liver, spleen and lymph node imaging, the x-ray contrast compositions of this invention are also expected to be useful as an angiographic contrast media, urographic contrast media, myelographic contrast media, gastrointestinal contrast media, cholecystographic and cholangiographic contrast media, arthrographic contrast media, hysterosalpingographic contrast media, oral contrast media and bronchographic contrast media.

The dose of the contrast agent to be administered can be selected according to techniques known to those skilled in the art such that a sufficient contrast enhancing effect is obtained. Typical doses can range from 50 to 350 mg of iodine per kilogram of body weight of the subject for many imaging applications. For some applications, e.g., lymphography, lower doses, e.g., 0.5-20 mg I/kg, can be effective.

The x-ray contrast composition can contain one or more conventional additives used to control and/or enhance the properties of the x-ray contrast agent. For example, thickening agents such as dextran or human serum albumin, buffers, viscosity regulating agents, suspending agents, peptizing agents, anti-clotting agents, mixing agents, and other drugs and the like can be added. A partial listing of certain specific additives includes gums, sugars such as dextran, human serum albumin, gelatin, sodium alginate, agar, dextrin, pectin and sodium carboxymethyl cellulose. Such additives, surface active agents, preservatives and the like can be incorporated into the compositions of the invention.

This invention further relates to a method of marking nanoparticles having a nonionic block copolymer of ethylene

-13-

oxide and butylene oxide adsorbed on the surface thereof, comprised of contacting said diagnostic or therapeutic agent with a block copolymer of ethylene oxide and butylene oxide for a time and under conditions sufficient to form a
5 stabilized nanoparticle. Contacting can be by admixing a suspension of the diagnostic or therapeutic agent with a solution of the block copolymer such as described above.

The following examples further illustrate the invention.

10 Examples 1-4 and Comparative Examples A-D

The following formulations were prepared at 15% diagnostic agent and 4% surfactant (w/v). A 6% stock solution was prepared by dissolving 600 mg B20-3800 or B20-
15 5000 surfactants in 10 ml deionized water. To each 15 ml amber colored bottle, 7.5 ml ZrSi beads of size 1.1 mm, 562 mg of Compound A or Compound B, 2.5 ml of 6% stock surfactant solution and 0.994 ml deionized water were added. The sample
20 bottle was sealed and placed on a roller mill running at 160 rpm for 5 days. At day 5, aliquot of samples were diluted 50 fold with deionized water for particle size measurement by photon correlation spectroscopy (PCS).

Example	Core	Surfactant	Mean Particle Size (nm)
1	Compound A	B20-5000	106
2	Compound A	B20-3800	110
A	Compound A	F108	130
B	Compound A	T908	241
3	Compound B	B20-5000	102
4	Compound B	B20-3800	94
C	Compound B	F108	140
D	Compound B	T908	144

25 This data demonstrates that the ethylene oxide-butylene oxide surfactant resulted in unexpectedly reduced mean

-14-

particle size compared to F108 and T908 when milled with two different x-ray contrast agent cores, i.e., ethyl 3,5-diacetoamido-2,4,6-triodobenzoate and 6-ethoxy-6-oxohexyl-3,5-bis(acetamido)-2,4,6-triodobenzoate, under identical
5 milling conditions.

In addition, tail vein injection of a 2% solution of B20-5000 at 0.05 ml/mice (n=3) and 0.5 ml/mice (n=3) was well tolerated by mice.

B20-3800 was tested in a smudge cell assay according to
10 the following procedure. This technique has been developed in order to evaluate the in vitro effect of surfactant on the lymphocytes in whole blood. Into each well of a round bottom 96 well microtiter plate is pipetted 225 μ l of whole human blood and 25 μ l of surfactant solution at the desired
15 concentration. The plate is placed on a blood rocker for two hours at room temperature to incubate the surfactant/blood mixture. After incubation, a small drop of the surfactant/blood mixture is placed on a glass slide and a wedge-prep blood smear is made on the slide. The smears are
20 air dried, and contacted with ethanol to fix the smear, and subsequently stained with Wright-Giemsa stain, available from Sigma Chemical. Lymphocytes with damaged or broken cell membranes which appear on the slide as smudge cells are counted as a percentage of the total leukocytes seen. An
25 average smudge cell count greater than 15 is considered a statistically significant positive smudge cell effect. B20-3800 was evaluated in the above-described smudge cell assay at concentrations of 10, 1 and 0.001% (v/v). Control A contained sterile water (no surfactant) and Control B
30 contained 1% T908. The test results were as follows:

-15-

Sample	Average Smudge Cel Count	Average Intact Lymphocyte Count
Control A (no surfactant	1.5	26.5
Control B T908 (1%)	19.0	9.0
B20-3800 (10%)	2.5	23.0
B20-3800 (1%)	6.0	21.5
B20-3800 (0.001%)	8.0	16.0

The data show that B20-3800 exhibited a significantly lower average smudge cell count and a higher average intact lymphocyte count compared to the T908 control even at a 10 times greater concentration.

B20-5000 coated on polystyrene particles also significantly inhibited the phagocytosis of such particles by macrophages while B20-3800 demonstrated a less dramatic effect. The ability of surfactant coated polystyrene particles to inhibit macrophage uptake was tested according to the procedure described by E. Liversidge et al in "Direct Suppression of Phagocytosis by Amphiphatic Polymer Surfactants", Pharm. Res.; Vol. 9, No. 9, pp. 1177-83. The number of particles measured per cell for B20-5000 surfactant coated polystyrene particles was about 3,000; about 28,000 for B20-3800 surfactant coated particles, and about 47,000 for the naked polystyrene particle control. In other words, B20-5000 exhibited about 95% reduction in macrophage uptake compared to control and the B20-3800 exhibited about 40% reduction.

Examples 5-6

In a procedure similar to that described in Examples 1-4 above, Danazol was milled in conjunction with B20-5000 and B20-3800. The mean particle size measured by PCS was 196 nm and 189 nm, respectively.

-16-

The invention has been described in detail with particular reference to certain preferred embodiments thereof, but it will be understood that variations and modifications can be effected within the spirit and scope of
5 the invention.


-17-

Claims:

1. A composition comprised of nanoparticles containing a therapeutic or diagnostic agent having a nonionic polymeric
 5 surfactant as a surface modifier adsorbed on the surface thereof, wherein said surfactant is a block copolymer of ethylene oxide and butylene oxide.

2. The compositions of claim 1 wherein said polymer has a
 10 molecular weight of 3,000-5,000.

3. The compositions of claim 1 wherein said surfactant is a triblock copolymer having the structure



15

wherein R is H or an active hydrogen group, x and y are 15-700; and, z is 5-200.

4. The composition of claim 1 wherein said polymer
 20 comprises at least 50% by weight of ethylene oxide units.

5. The composition of claim 1 wherein said diagnostic agent is ethyl 3,5-diacetoamido-2,4,6-triiodobenzoate.

25 6. The composition of claim 1 wherein said diagnostic agent is 6-ethoxy-6-oxohexyl-3,5-bis(acetamido)-2,4,6-triiodobenzoate.

7. The composition of claim 1 wherein said therapeutic
 30 agent is Danazol.

8. A method of making nanoparticles containing a diagnostic or therapeutic agent having a nonionic block copolymer of ethylene oxide and butylene oxide adsorbed on the surface
 35 thereof comprised on contacting said diagnostic or

-18-

therapeutic agent with a block copolymer of ethylene oxide and butylene oxide for a time and under conditions sufficient to form a stabilized nanoparticle.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/07406

A. CLASSIFICATION F SUBJECT MATTER
IPC 6 A61K9/14 A61K9/51

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 499 299 (STERLING WINTHROP INC.) 19 August 1992 see the whole document & US,A,5 145 684 cited in the application ---	1-8
A	CHEMICAL ABSTRACTS, vol. 110, no. 20, 15 May 1989 Columbus, Ohio, US; abstract no. 179465v, J.H. LEE ET AL. 'PROTEIN-RESISTANT SURFACES PREPARED BY PEO-CONTAINING BLOCK COPOLYMER SURFACTANTS' page 408; column 1; see abstract & J. BIOMED. MATER. RES., vol. 23, no. 3, 1989 pages 351-368, ---	1-8
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *&* document member of the same patent family

Date of the actual completion of the international search

27 October 1995

Date of mailing of the international search report

10. 11. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Benz, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 95/07406

C(Continuation) D CUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR,A,2 557 812 (THE DOW CHEMICAL COMPANY) 12 July 1985 see the whole document -----	1-8

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/07406

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-499299	19-08-92	US-A- 5145684	08-09-92
		AU-B- 642066	07-10-93
		AU-B- 1014592	30-07-92
		AU-B- 654836	24-11-94
		AU-B- 1014792	30-07-92
		EP-A- 0498482	12-08-92
		JP-A- 4317053	09-11-92
		JP-A- 4295420	20-10-92
		US-A- 5399363	21-03-95
		US-A- 5318767	07-06-94
FR-A-2557812	12-07-85	AU-B- 3835685	30-07-85
		CA-A- 1252016	04-04-89
		DE-T- 3590005	13-03-86
		EP-A, B 0167621	15-01-86
		GB-A, B 2152490	07-08-85
		SE-B- 453260	25-01-88
		SE-A- 8504178	09-09-85
		WO-A- 8503065	18-07-85